

# Densification, grain growth and texturation in SPS nanoZnO ceramics.

**Fabien GIOVANNELLI<sup>(1)</sup>, Pablo DIAZ-CHAO<sup>(2,3)</sup>, Oleg LEBEDEV<sup>(2)</sup>, Daniel CHATEIGNER<sup>(2)</sup>, Emmanuel GUILMEAU<sup>(2)</sup>, Fabian DELORME<sup>(1)</sup>**

<sup>1</sup> Université François Rabelais de Tours, CNRS, INSA CVL, GREMAN UMR 7347, IUT de Blois, 15 rue de la chocolaterie, 41029 Blois Cedex, France.

<sup>2</sup> CRISMAT, UCBN, ENSICAEN, 6 Boulevard du Maréchal Juin, 14050 Caen Cedex, France.

<sup>3</sup> Present address: National Physical Laboratory, Materials Division, Hampton Road, Teddington, Middlesex, United Kingdom.

Contact author: fabien.giovannelli@univ-tours.fr

ZnO and 0.3 at% Al-doped ZnO nanoparticles have been synthesized by precipitation. An aqueous soda solution has been added to a zinc nitrate (or zinc nitrate and aluminum chloride) aqueous solution at room temperature under vigorous stirring according to the route developed by Giovannelli et al. [1]. The two samples are mostly composed by plate-like nanoparticles circa 200-400 nm large and a few tens of nanometers thick with the c-axis in plane according to TEM images and electron diffraction. The 0.3 at% Al-doped sample also exhibits nanoparticles of few tens of nanometers exhibiting an isotropic shape. Moreover, plate-like nanoparticles of the pure ZnO sample are agglomerated as sand roses. Then the powders have been densified by Spark Plasma Sintering (SPS) at temperatures ranging from 400°C to 1100°C under a pressure of 100M Pa. Their behaviour is completely different: 0.3 at% Al-doped ZnO nanoparticles reach high densities (> 95 %) since 500°C whereas pure ZnO requires temperature beyond 1000°C. The microstructures are also different. The grains of the 0.3 at% Al-doped ZnO remain nanosized at 500°C but are close to micrometer since 600°C. For the pure ZnO grain growth starts only near 1000°C. After starting growing, the grains present an isotropic shape. The quantitative X-ray diffraction texture analysis [2, 3] shows that the ceramics present a crystallographic texture with the c-axis perpendicular to the pressure application direction. The evolution of this texture has been studied over the whole temperature range for the two compositions.

[1] F. Giovannelli, A. Ngo Ndimba, P. Diaz-Chao, M. Motelica-Heino, P.I. Raynal, F. Delorme. Powder Technology 262 (2014) 203-208.

[2] L. Lutterotti, S. Matthies, H.R. Wenk. MAUD (Material Analysis Using Diffraction): a user friendly Java program for Rietveld texture analysis and more. Spunar J.A. (Ed.). National Research Council of Canada, Ottawa, 1599 (1999).

[3] D. Chateigner. Combined analysis, Ed. Wiley-ISTE, London, 496 pages (2010).